

Lead Shield

Post-Removal Lockdown/Sealant

Product Description

Lead Shield is a water based 100% acrylic lockdown with a dual purpose; it binds residual lead-based paint and dust present after removal; and accepts most topical coverings. The clear version of this product sprays on white and dries clear to permit visual inspection of any residual paint. The translucent blue tint speeds up the post removal inspection process after the product has fully cured. The blue tint is advantageous because it enables an inspector to quickly identify areas that LBP has been removed from and subsequently locked down. These unique features assist in obtaining final LBP removal certification. Lead Shield is a one step product which bonds to most surfaces eliminating the need for sanding, priming and sizing recently stripped walls. Lead Shield can be used on both interior and exterior surfaces, and was expressly formulated to prepare these surfaces to accept a final topical covering. Lead Shield should not be used as a substitute for encapsulation.

5470-Clear, 5475-Translucent Blue, 5477-White

Application Information

SURFACE PREPARATION

Warning! If you scrape, sand, or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Carefully clean up with a wet mop and HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

Lead Shield must be applied when the atmosphere and surface temperatures exceed 50°F. Surfaces must be free of all surface contamination prior to application of Lead Shield. Patch any irregularities with vinyl patching paste or appropriate patching compound. If chemical strippers were used to remove the paint, follow the manufacturers' suggestions for surface cleaning before applying Lead Shield. Sanding, scraping and other surface preparation procedures can create toxic dust and hazardous waste. A HEPA (High Efficiency Particulate Air) vacuum should be used on all surfaces to remove hazardous dust and particles. Use MSHA/NIOSH approved or equivalent respiratory protection suitable for concentrations and types of air contaminants encountered.

APPLICATION TOOLS & PROCEDURES

Consult all related local, state, and federal regulations regarding work practices and personal protection prior to the application of Lead Shield. Do not apply when air or surface temperature is below 50°F or when drying conditions are poor. Lead

Shield is supplied ready to use. Apply Lead Shield uniformly by brush, roller, or spray. Stir thoroughly to achieve a uniform consistency before selecting one of the recommended application methods below.

TOOLS

Brush: Synthetic, nylon or polyester
 Roller: 3/8" nap synthetic fiber
 Spray Settings:
 Pressure: 2000-3000 P.S.I.
 Tips: .015 to .021 tips

MIXING

Mix thoroughly. Do not add solvents, oils or colors in oil, or mix with other paint types.

DRYING TIME @ 70°F 50% R.H.

To Touch – 30 minutes
 Recoat – 2 hours

COVERAGE

Smooth Surfaces- 450 sq. ft. per gallon
 Porous Surfaces- 100-300 sq. ft. per gallon

CLEAN UP

Clean tools and drippings with warm soapy water before Lead Shield dries. Dispose of all waste according to all existing local, state and federal regulations.

Properties

Product Specifications

Solids by Weight ± 2%:	29.0%
Solids by Volume ± 2%:	26.1%
Viscosity at 70°F:	85-90 Krebs Units
Specular Gloss:	35-40° @ 60°
Flash Point:	Non-combustible
Shelf Life:	36 Months Min. (Original Sealed Containers)
Calculated VOC:	96 grams/liter

*Lead Shield Calculated VOC dependent on color

Coverage

Smooth Surfaces:	450 ft ² /gal
Porous Surfaces:	100-300 ft ² /gal

Drying Times (@ 70 - 77°F, 50% R.H.)

To Touch:	30 minutes
To Recoat:	2 hours
Min. Application Temperature:	50°F (10°C)

Available Package Sizes

5 gallon containers	
Weight Per Gallon ± .5 lbs:	8.71 lbs/gal

Product Testing

Fire Rating:	ASTM E84 Class A
Flame Spread:	5
Fuel Contribution:	0
Smoke Density:	15



Application Information

PRECAUTIONS

Store in a dry place at temperatures between 40°F (4.5°C) and 90°F (32°C). Stir thoroughly. Do not mix with any other coatings, solvents or colors in oil. Do not apply when air or surface temperature is below 50°F or when drying conditions are poor. Do not re-coat with coatings using aromatic or other strong solvents. When applying with a sprayer, wear a NIOSH approved respirator with any R, P,N or HE filter. Use adequate ventilation during application.

CAUTION!

KEEP OUT OF REACH OF CHILDREN.

Do not take internally. Close container after each use.

Keep from freezing.

Store between 40°F (4.5°C) and 90°F (32°C)

24 hour Emergency "CHEM-TEL" - 800.255.3924

For Technical Information call 800.342.3755

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of this product are beyond our control. Neither Fiberlock Technologies, Inc., nor its agents shall be responsible for the use or results of use of this product or any injury, loss or damage, direct or consequential. We recommend that the prospective user determine the suitability of this product for each specific project and for the health and safety of personnel working in the area.

Lead Shield, the Lead Shield Logo and other marks in this literature are trademarks of Fiberlock Technologies, Inc.